#### § 27.32

the official color grade. Cotton classers, designated as such by the Director, will determine the official leaf grade and extraneous matter, and authorized Cotton Program employees will determine all fiber property measurements using High Volume Instruments.

[65 FR 36598, June 9, 2000]

## § 27.32 Order of classification.

All cotton for which classifications requests shall be pending shall be classified as far as practicable in the order in which proper samples thereof, ready for such classification, shall have been delivered to the Marketing Services Office, except as otherwise provided in this subpart or when the Area Director or the Director shall find that an emergency exists and shall order otherwise.

[48 FR 49211, Oct. 25, 1983]

## § 27.33 Exposing of samples for classification.

Classification shall not proceed until the samples, after being delivered to the Marketing Services Office, shall have been exposed for such length of time as in the judgment of the Area Director shall be sufficient to put them in proper condition for the purpose.

[48 FR 49211, Oct. 25, 1983]

#### §27.34 Classification procedure.

Classification shall proceed as rapidly as possible, but not when light or other conditions make uncertain the accuracy of the results to be obtained.

# § 27.35 Lower class of two samples to prevail.

In case a sample drawn from one portion of a bale is lower in class than one drawn from another portion of such bale, except as otherwise provided in this subpart, the classification of the bale shall be that of the sample showing the lower class.

# § 27.36 Classification and Micronaire determinations based on official standards.

All cotton shall be classified for grade and staple length on the basis of the official cotton standards of the United States for grade and staple length in effect at the time of such

classification. Micronaire determinations for cotton, upon request under §27.14, §27.62, or §27.63 shall be made according to the official cotton standards of the United States for fiber fineness and maturity in effect at the time of such determinations.

#### § 27.37 Cotton reduced in grade.

If cotton be reduced in grade, by reason of the presence of extraneous matter or other irregularities or defects, below its grade according to the official cotton standards of the United States, the grade from which it is so reduced, and the condition or reason which so reduces its grade shall be determined and stated.

[25 FR 5872, June 25, 1960]

# § 27.38 Terms defined for purposes of classification.

For the purposes of classification the following terms shall be construed, respectively, to mean:

- (a) Cotton of perished staple. Cotton that has the strength of fiber as ordinarily found in cotton destroyed or unduly reduced through exposure to the weather either before picking or after baling, or through heating by fire, or on account of water packing, or by other causes.
  - (b) [Reserved]
- (c) Gin cut cotton. Cotton that shows damage in ginning, through cutting by the saws, to an extent that reduces its value more than two grades.
- (d) Reginned cotton. Cotton that has passed through the ginning process more than once, and cotton that, after having been ginned, has been subjected to a cleaning process and then baled.
- (e) Repacked cotton. Cotton that is composed of factors', brokers', or other samples, or of loose or miscellaneous lots collected and rebaled, or cotton in a bale which is composed of cotton from two or more smaller bales or parts of bales that are combined after the cotton leaves the gin.
- (f) False packed cotton. Cotton in a bale (1) containing substances entirely foreign to cotton, (2) containing damaged cotton in the interior with or without any indication of such damage upon the exterior, (3) composed of good cotton upon the exterior and decidedly inferior cotton in the interior, in such

manner as not to be detected by customary examination, or (4) containing pickings or linters worked into the bale.

(g) Mixed packed cotton. Cotton in a bale which, in the sample taken therefrom, shows (1) a difference of three or more grades, or (2) a difference of three or more color groups, or (3) a difference in length of staple of one-eighth inch or more. For purposes of this paragraph, White Cotton (including the Plus grades), Light Gray Cotton, and Gray Cotton shall constitute one color group, and Light Spotted Cotton, Spotted Cotton, Tinged Cotton, and Yellow Stained Cotton shall each constitute a color group.

(h) Water packed cotton. Cotton in a bale that has been penetrated by water during the baling process, causing damage to the fiber, or a bale that through exposure to the weather or by other means, while apparently dry on the exterior, has been damaged by water in the interior.

[22 FR 10926, Dec. 28, 1957, as amended at 26 FR 5945, July 1, 1961; 32 FR 7011, May 9, 1967; 35 FR 17935, Nov. 21, 1970]

## COTTON CLASS CERTIFICATES

### § 27.39 Issuance of certificates.

Except as otherwise provided in this section, as soon as practicable after the classification of cotton has been completed by a Marketing Services Office, the Marketing Services Office shall issue a cotton class certificate showing the results of such classification. Each certificate shall bear the date of its issuance and the name of the Area Director of the Marketing Services Office that classified the cotton. The certificate shall show the identification of the cotton according to the information in the possession of the Marketing Services Office, the classification of the cotton according to its grade and length of staple and such other facts as the Director may require. As soon as practicable after the Micronaire determination of cotton has been completed by an authorized employee of the Cotton Division, upon request under this subpart, the results of such determination shall be certified by the Marketing Services Office or by the Grading Section on the classification cer-

tificate for the cotton, with the date of issuance of the Micronaire determination, the name of the certifying officer, and such other facts as the Director may require. When a request is made for a review of classification and a Micronaire determination, at the same time as the request for initial classification, the Marketing Services Office shall notify the Grading Section of the results of the classification and the latter shall review the classification and make the Micronaire determination. and notify the Marketing Services Office of the results. The latter shall issue a cotton class certificate over the signature of the Head, Grading Section showing the results of the review classification (but not the initial classification), the Micronaire determination, the date of issuance of the certificate, and such other facts as the Director may require. The certificate of classification and Micronaire determination may be placed directly upon the warehouse receipt covering the cotton involved. The Marketing Services Office or the Grading Section may authorize an officer of the Service located at another point to certify the results of any classification or Micronaire determination upon the basis of information furnished by them, notwithstanding any other provisions of this section.

[48 FR 49211, Oct. 25, 1983]

## § 27.40 New certificates; conditions of issuance.

For the business convenience of a holder of a cotton class certificate issued under this subpart a new certificate may be issued at the request of the holder, to take the place of the former certificate without the reclassification of the cotton and without a new Micronaire determination for the cotton. In any case where a new certificate is issued in accordance with this section, the former certificate shall be surrendered for cancellation, and such new certificate shall bear a new number, the date of its issuance, and the date of original certification, and shall otherwise comply with this subpart.